


Range: Bowral 50

Colour:

SKU: 280070042490000125100



## Technical Data

Width (mm)	110
Height (mm)	50
Depth (mm)	230
Dimensional Category	DW1
Core Volume (%)	Solid
Units per Square Metre	69.5
Pack Size	700
Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	>8
Maximum Cold Water Absorption (%)	15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1 to 8

Coefficient of Expansion e'Factor (mm/m)	1.2
Liability to Efflorescence	Nil to slight
Lime Pitting Liability	Nil to slight
Solar Absorption	0.584
LRV	33.33
Basix	Medium
Place of Manufacture	New South Wales
Product Warranty	100 Years
Solar Absorption	0.584
Weight	2.5

This Data represents average results from commercial production lots. If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE. January 2025

[www.brickworks.co.nz](http://www.brickworks.co.nz)

A BRAND OF

**BRICKWORKS**