

Range: Bowral 76
Colour:
SKU: 280080010780000136100



Technical Data

Width (mm)	110
Height (mm)	76
Depth (mm)	230
Dimensional Category	DW1
Core Volume (%)	Solid
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f 'uc) MPa	>8
Maximum Cold Water Absorption (%)	15
Initial Rate of Absorption (IRA) (kg/m2 min)	1 to 8

Liability to Efflorescence	Nil to slight
Lime Pitting Liability	Nil to slight
Solar Absorption	0.343
LRV	66.44
Basix	Light
Place of Manufacture	New South Wales
Product Warranty	100 Years
Solar Absorption	0.343
Meter squared	48.5
Weight	3.8

Coefficient of Expansion e'Factor (mm/m) 1.2
This Data represents average results from commercial production lots. If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE. January 2025
www.brickworks.co.nz